

# TECHNICAL DATA SHEET KI-ROHS

# **ROHS COMPLIANCE GENERAL PURPOSE PVC INSULATION COMPOUND**

**DESCRIPTION:** KI-ROHS is specially formulated PVC Compound MEET IS-5831 TYPE -A FOR BUILDING WIRE & CABLE APPLICATION. It is a General purpose insulation intended for using cables operating at a maximum rated conductor temperature 70°C. The compound will meet the requirement of ROHS compliance.

## **CHARACTERISTICS :**

- Good surface smoothness
- Excellent electrical properties.
- Long run Extrusion without Thermal degradation
- Good physical and thermal property.
- Balances of properties and processability.

#### **SPECIFICATION**:

This compound will meet TYPE-'A' of IS-5831

### PROPERTY ( PHYSICAL ) :

Properties	Unit	Requirement As Per IS-5831	Typical value*
Specific gravity	-	Not Applicable	1.33±0.03
Shore hardness	"A"	Not Applicable	89 <u>+</u> 2
Before Ageing Tensile strength	N/mm2	12.5 (min)	17.0
Before Ageing Elongation at break	%	150 (min)	290
After ageing @ 80°C ± 2°C for 7 days			
After Ageing Tensile strength	%	12.5(min)	16.6
Variation in Tensile strength	%	± 20	-2.35
After Ageing Elongation at break	%	<b>150(min)</b>	275
Variation in Elongation	%	± 20	-5.17
Thermal Stability @ 200°C ± 0. 5°C	Minutes	<b>80</b> (min)	110
Volume Resistivity @ 27°C	Ohm-cm	$1 \times 10^{13} (min)$	3.0X10 <sup>14</sup>
LOSS OF MASS	Mg/cm <sup>2</sup>	<b>2(max)</b>	0.4

\*\*\* The properties have been tested on moulded sheet

# **PROCESSING TECHNIQUES:**

- 1. The recommended processing temperatures are 150<sup>o</sup>c to 180<sup>o</sup>c , However the processing Temperature may be adjusted as per requirement for individual operations.
- 2. KI- ROHS provides excellent surface finish and outstanding output rates over a broad range of extrusion running condition .
- **3.** For smooth processing and better results it is recommended to preheat the material before use.
- 4. Specific processing condition depend on equipments and cable dimensions.

**DELIVERY/PACKAGES** : Pellet form and packed in 25 kg HDPE woven sacks with inner liner to ensuring prevention from uptake of moisture and contamination.

#### STORAGE:

Material shall be kept in a cool dry place.

(The information given in the document is believed to be reliable and is given in good faith but without warranty. The user should test the product to assertion the suitability for intended use. The product specification or the whole document is subject to change without any prior notice.)

FOR MORE INFORMATION PL CONTACT AT : Head Office: 2B Pretoria Street, Kolkata-01 Tel: 91-33-22823744/45/3671 Fax:91-33-22823739 E-mail: <u>kolkata@kkalpana.co.in</u> Website:<u>www.kkalpanagroup.com</u>